



PAINT CORRECTION PROCESS

with the MT300 DUAL ACTION POLISHER



MT300
Dual Action Polisher

QUESTIONS?

Call the Surface Care Specialists at Meguiar's
1-800-347-5700



PAINT CORRECTION PROCESS

With the MT300 Dual Action Polisher

Select the condition of your paint



New or like-new
Good gloss, NO swirls or oxidation



Average
Light swirls, scratches, or oxidation



Neglected
Moderate swirls, scratches, oxidation and stains

BEFORE YOU BEGIN:

Prepare your paint surface by washing the vehicle using a premium car wash such as **Meguiar's® Ultimate Wash & Wax**. After washing and drying your vehicle if the paint surface feels rough to the touch, we recommend using our **Smooth Surface™ Clay Kit** prior to compounding, polishing, or waxing. For more information on proper washing techniques or using our Smooth Surface™ Clay Kit please visit our website at **www.meguiars.com** or contact our **Surface Care Specialists at 800-347-5700**.

1. Wash your vehicle



2. Clay your vehicle

(If needed)



NEXT:

After completing the above steps, you are ready to start using your new Meguiar's MT300 Dual Action Polisher.

Be sure to securely attach **Meguiar's 5 inch Soft Buff DA Backing Plate (DBP5)** with the included wrench. Please be sure you read, understand and follow all the instructions provided in the MT300 Owner's Manual.





PAINT CORRECTION PROCESS

With the MT300 Dual Action Polisher

PAINT

NEW OR LIKE-NEW

CONDITION: Good gloss, NO swirls or oxidation



STEP 1. Wax

Items needed:



MT300



Ultimate Liquid Wax



Finishing Disc



Microfiber Towel

- A.** Dispense a small amount of **Meguiar's Ultimate Wax** onto a clean **Black Foam DA Finishing Disc (DFF5)**.
- B.** Set **MT300 Polisher speed to 3800 OPM**. Apply 2 overlapping passes using light pressure. Apply more product as needed until all painted surfaces of the vehicle are covered in a thin uniform coat.
- C.** Wipe off residue with a clean **Meguiar's Supreme Shine Microfiber Towel**.



PAINT CORRECTION PROCESS

With the MT300 Dual Action Polisher

PAINT CONDITION: **AVERAGE**
Light swirls, scratches or oxidation



STEP 1. Polish

Items needed:



MT300



Ultimate Polish



Polishing Disc



Microfiber Towel

A. Dispense a small amount of **Meguiar's Ultimate Polish** onto a clean **Yellow Foam DA Polishing Disc (DFP5)**.

B. Set **MT300 Polisher speed to 4800 OPM**. Work in a 2'X2' section and apply 2 – 3 overlapping passes using moderate pressure. (Do not allow product to dry.)

C. Wipe off residue using a clean **Meguiar's Supreme Shine Microfiber Towel**.

STEP 2. Wax

Items needed:



MT300



Ultimate Liquid Wax



Finishing Disc



Microfiber Towel

A. Dispense a small amount of **Meguiar's Ultimate Wax** onto a clean **Black Foam DA Finishing Disc (DFF5)**.

B. Set **MT300 Polisher speed to 3800 OPM**. Apply 2 overlapping passes using light pressure. Apply more product as needed until all painted surfaces of the vehicle are covered in a thin uniform coat.

C. Wipe off residue with a clean **Meguiar's Supreme Shine Microfiber Towel**.



PAINT CORRECTION PROCESS

With the MT300 Dual Action Polisher

PAINT

CONDITION:

NEGLECTED

Moderate swirls, scratches, oxidation and stains



STEP 1. Compound

Items needed:



MT300



Ultimate Compound



Cutting Disc



Microfiber Towel

- Dispense a small amount of **Meguiar's Ultimate Compound** onto a clean **Red Foam Cutting Disc (DFC5)**.
- Set **MT300 Polisher speed to 5800 OPM**. Work in a 2'X2' Section and apply 3-4 overlapping passes using moderate pressure, moving the pad slowly across the paint. Re-apply as needed to remove stubborn defects. (Do not allow product to dry.)
- Wipe off residue using a clean **Meguiar's Supreme Shine Microfiber Towel**.

STEP 2. Polish

Items needed:



MT300



Ultimate Polish



Polishing Disc



Microfiber Towel

- Dispense a small amount of **Meguiar's Ultimate Polish** onto a clean **Yellow Foam DA Polishing Disc (DFP5)**.
- Set **MT300 Polisher speed to 4800 OPM**. Work in a 2'X2' section and apply 2 - 3 overlapping passes using moderate pressure. (Do not allow product to dry.)
- Wipe off residue using a clean **Meguiar's Supreme Shine Microfiber Towel**.

STEP 3. Wax

Items needed:



MT300



Ultimate Liquid Wax



Finishing Disc



Microfiber Towel

- Dispense a small amount of **Meguiar's Ultimate Wax** onto a clean **Black Foam DA Finishing Disc (DFF5)**.
- Set **MT300 Polisher speed to 3800 OPM**. Apply 2 overlapping passes using light pressure. Apply more product as needed until all painted surfaces of the vehicle are covered in a thin uniform coat.
- Wipe off residue with a clean **Meguiar's Supreme Shine Microfiber Towel**.